



RESIN FOR FIBER

纖維用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
AT-45-2	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	45±1	<300	7~9	26	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water, Solvent Resistance and Mechanical Stability 耐水性、耐溶劑性與機械安定性良好
AT-45U	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	45±1	<100	2~3	39	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water, Solvent Resistance and Mechanical Stability 耐水性、耐溶劑性與機械安定性良好
AT-40	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	<100	7~9	26	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water, Solvent Resistance and Mechanical Stability 耐水性、耐溶劑性與機械安定性良好
AT-40-2	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	<100	7~9	25	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water, Solvent Resistance and Mechanical Stability 耐水性、耐溶劑性與機械安定性良好
AT-40-2H	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	<100	7~9	30	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water, Solvent Resistance and Mechanical Stability 耐水性、耐溶劑性與機械安定性良好
ST-40-2	Self-Crosslinking Styrene-Acrylic Copolymer 自己架橋型苯乙烯-壓克力共聚樹脂	White Emulsion 白色乳液	40±1	<100	7~9	32	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water Resistance and Mechanical Stability 耐水性與機械安定性良好
ST-40-2H	Self-Crosslinking Styrene-Acrylic Copolymer 自己架橋型苯乙烯-壓克力共聚樹脂	White Emulsion 白色乳液	40±1	<100	7~9	36	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water Resistance and Mechanical Stability 耐水性與機械安定性良好
ST-40UF	Self-Crosslinking Styrene-Acrylic Copolymer 自己架橋型苯乙烯-壓克力共聚樹脂	White Emulsion 白色乳液	40±1	<100	7~9	46	Binder for Hard Type Non-Woven Fabrics, Suitable for Spray and Dipping 不織布用硬質膠料，適合噴霧浸漬加工	Excellent Water Resistance and Mechanical Stability 耐水性與機械安定性良好
M-19	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	<100	5~7	18	Binder for Semi-Hard Type Non-Woven Fabrics 不織布用中硬質膠料	Excellent Solvent Resistance and Mechanical Stability 耐溶劑性與機械安定性良好
A-45U	Self-Crosslinking Styrene-Acrylic Copolymer 自己架橋型苯乙烯-壓克力共聚樹脂	White Emulsion 白色乳液	45±1	<100	2~3	0	Binder for Semi-Hard Type Non-Woven Fabrics 不織布用中硬質膠料	Low pH Value, Excellent Water, Solvent Resistance and Mechanical Stability 低pH值，耐水性、耐溶劑性與機械安定性良好
A-410	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	45±1	<500	4~6	<0	Binder for Soft Non-Woven Fabrics 不織布用軟質膠料	Flexible and Elastic, Excellent Water Resistance and Mechanical Stability 柔軟，彈性好，耐水性與機械安定性良好
A-404	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	Slightly Yellowish Transparent Emulsion 淡黃透明乳液	40±1	400±200	5~6	<0	Binder for Soft Non-Woven Fabrics 不織布用軟質膠料	Flexible and Elastic, Excellent Water Resistance and Mechanical Stability 柔軟，彈性好，耐水性與機械安定性良好
A-425	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	Slightly Yellowish Transparent Emulsion 淡黃透明乳液	40±1	800±200	5~6	<0	Binder for Soft Non-Woven Fabrics 不織布用軟質膠料	Flexible and Elastic, Excellent Water Resistance and Mechanical Stability 柔軟，彈性好，耐水性與機械安定性良好



RESIN FOR FIBER

纖維用樹脂

ST-404U	Self-Crosslinking Styrene-Acrylic Copolymer 自己架橋型苯乙烯-壓克力共聚合樹脂	White Emulsion 白色乳液	40±1	<100	5~6	<0	Binder for Soft Non-Woven Fabrics 不織布用軟質膠料	Flexible and Elastic, Excellent Water Resistance and Mechanical Stability 柔軟，彈性好，耐水性與機械安定性良好
ST-330F	Self-Crosslinking Styrene-Acrylic Copolymer 自己架橋型苯乙烯-壓克力共聚合樹脂	Transparent Emulsion 透明乳液	40±1	800±150	6~8	<0	Binder for Soft Non-Woven Fabrics 不織布用軟質膠料	Flexible and Elastic, Excellent Water Resistance and Mechanical Stability 柔軟，彈性好，耐水性與機械安定性良好
A-420H	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	<100	7~8	10	Binder for Soft Non-Woven Artificial Leather Lining 不織布仿裡皮製造用之軟質樹脂	Excellent Chemical Stability and Electrolyte Resistance 具優良之化學安定性，耐電解質
A-420	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	<100	7~8	<0	Binder for Soft Non-Woven Artificial Leather Lining 不織布仿裡皮製造用之軟質樹脂	Excellent Chemical Stability and Electrolyte Resistance 具優良之化學安定性，耐電解質
MC-11	Styrene Resin 苯乙烯樹脂	White Emulsion 白色乳液	45±1	<200	7~9	90	Binder for Shoe Toe Lining 鞋襪用膠料	Will Has Tack When Dipping with Toluene, Super Hard and Good Moulding Nature 以甲苯含浸會產生粘性，硬度大，成型性良好
MC-12T	Reactant Styrene Acrylic Copolymer 反應型苯乙烯壓克力共聚合樹脂	Slightly Yellowish Transparent Emulsion 淡黃透明乳液	40±1	<100	7~9	56	Binder for Shoe Insole 中底皮用膠料	Will Has Tack When Dipping with Toluene, Super Hard and Good Moulding Nature 以甲苯含浸會產生粘性，硬度大，成型性良好
MC-12NT	Reactant Styrene Acrylic Copolymer 反應型苯乙烯壓克力共聚合樹脂	Slightly Yellowish Transparent Emulsion 淡黃透明乳液	45±1	<300	7~9	52	Binder for Hard Moulding Nature Type 硬質成型用膠料	No Tack When Dipping with Toluene, Super Hard and Good Moulding Nature 浸甲苯後無粘性，硬度大，成型性良好