

ITEM NO.	MAIN COMPONENT	FORM	SOLID CONTENT (%)	VISCOSITY (CPS)	РН	M. F. T. (°C)	MAIN USES	SPECIAL FEATURES
P-50	LACTVIIC Resin	White Emulsion	50±1	<100	8~10	10		Good Brushability, Weather & Water Resistance and Pigment Miscibility
P-57A	LActivite Resin	White Emulsion	46±1	2000±500	7~9	15		High Film Gloss, Good Brushability, Weather and Water Resistance and Pigment Miscibility
P-57AH	LActivite Resin	White Emulsion	50±1	10000±2000	7~9	15		High Film Gloss, Good Brushability, Weather and Water Resistance and Pigment Miscibility
P-62A	LActviic Resin	White Emulsion	55±2	2000±500	6~8	15		High Solid Content, High Film Gross, Good Brushability, Water Resistance and Pigment Miscibility
P-60	LAcrylic Resin	White Emulsion	60±1	2500±500	5~7	0		High Solid Content, Soft and Elastic Film, Good Pigment Miscibility
P-/301	Styrene Acrylic Copolymer	White Emulsion	46±1	2000±500	7~9	15	Based Paint	High Film Gloss, Good Brushability, Water and Water Resistance and Pigment Miscibility
AC-5050	Wintel Acatata Racin	White Emulsion	50±1	10000±2000	2~4	12	Binder for Interior Water Based Paint	Good Brushability and Pigment Miscibility
P-550S	,	White Emulsion	50±1	6000±2000	3~5	11		High Film Gloss, Good Brushability, Water Resistance and Pigment Miscibility
B-3000	Acrylic Resin	Brown Liquid	50±1	2000±1000	6~8	-	Binder for Baking Paint	Good Water Solubility