

ITEM NO.	MAIN COMPONENT	FORM	SOLID CONTENT (%)	VISCOSITY (CPS)	РН	Ti	MAIN USES	SPECIAL FEATURES
AR-165	Acrylic Resin	White Emulsion	50±1	400 ±100	6~8	5	Adhesive for Removal	Suitable for Many Kinds of Substrates, Good Cohesion and Removable Properties
AR-185	Acrylic Resin	White Emulsion	40±1	<500	6~8	5		Suitable for Many Kinds of Substrates, Good Cohesion and Removable Properties
AR-195	Acrylic Resin	White Emulsion	40±1	<500	6~8	5	Adnesive for Removal	Suitable for PET film, Good Cohesion and Removable Properties
AR-625M	Acrylic Resin	White Emulsion	35±1	750±250	6~8	5		Suitable for Many Kinds of Substrates, Good Cohesion and Removable Properties, Long Retention of Surface Tack
AR-673P	Acrylic Resin	White Emulsion	50±1	14500±1000	5.5~7.5		PVC Sheet	Excellent Bonding Strength, Creep Resistance and High Tack
AR-673H	Acrylic Resin	White Emulsion	50±1	24000±1000	6~8	>h	PVC Sheet	Excellent Bonding Strength, Creep Resistance and High Tack
AR-681	Acrylic Resin	White Emulsion	55±1	8000±1000	6~8		Paper Label	High Solid Content, Good Creep Resistance
AR-683V-1	Acrylic Resin	White Emulsion	55±1	8000±1000	6~8	3 h~ 3 X		Suitable for PE Substrates, Good Adhesion and Cohesion Properties, High Tack
AR-683P-1	Acrylic Resin	White Emulsion	55±1	8000±1000	6~8	3.6~3.8	film	Suitable for Many Kinds of Substrates, Good Adhesion and Cohesion Properties, High Tack
AR-685	Acrylic Resin	White Emulsion	55±1	750±250	6~8	5~5.5	OPP Tape	Excellent Bonding Strength, Creep Resistance and High Tack
AR-686B	Acrylic Resin	White Emulsion	55±1	150±100	6~8	5		Excellent Bonding Strength, Creep Resistance and High Tack
AR-690H	Acrylic Resin	White Emulsion	60±1	5000~6000 (RVT) 8000±1000 (LVT)	6~8	>4	Double Side Type	High Solid Content, Excellent Bonding Strength, Creep Resistance and High Tack
AR-696	Acrylic Resin	White Emulsion	60±1	<200	6~8		Pressure Sensitive Adhesive for OPP Tape	High Solid Content, Excellent Bonding Strength, Creep Resistance and High Tack, Non-Yellowing Type