



# LEATHER CHEMICALS

## 皮革用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-1740	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	White Emulsion 白色乳液	40±1	< 100	7~9	22	Binder for Leather Finishing 皮革表面處理之膠料	Hard Type, High Gloss, Excellent Pigment Compatibility and Leather Adhesion 硬型，高光澤，顏料相容性佳，對皮革附著力良好
L-1742	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	Slightly Yellowish Transparent Emulsion 淡黃透明乳液	35±1	< 100	4~6	0	Binder for Leather Finishing 皮革表面處理之膠料	Soft Type, Good Solvent Resistance, Excellent Pigment Compatibility, Flexibility, Good Adhesion 軟型，耐溶劑性良好，顏料相容性佳，彈性好，對皮革附著力良好
L-1743	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	Slightly Yellowish Transparent Emulsion 微黃透明乳液	35±1	< 100	4~6	0	Binder for Leather Finishing 皮革表面處理之膠料	Medium Soft, Excellent Water and Solvent Resistance, Pigment Compatibility, Flexibility, Leather Adhesion 中軟型，耐水性及耐溶劑性良好，顏料相容性佳，彈性好，對皮革附著力良好
L-1747	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	Slightly Yellowish Transparent Emulsion 淡黃透明乳液	35±1	< 100	4~6	0	Binder for Leather Finishing 皮革表面處理之膠料	Soft Type, Fine Particle Size, Good Wet Rub Property and Good Solvent Resistance, Excellent Pigment Compatibility, Flexibility, Good Adhesion 軟型，粒子徑小，濕磨特性，耐溶劑性良好，顏料相容性佳，彈性好，對皮革附著力良好
L-1749	Self-Crosslinking Acrylic Resin 自己架橋型壓克力樹脂	Yellow Transparent Emulsion 黃色透明乳液	12±1	< 100	8~9	0	Binder for Leather Re-pigment Finishing 再塗性皮革用之膠料	Soft Type, Very Good Flexibility and Elasticity, Suitable for Repigment 軟型，富於彈性，接著力強，尤適用於色改