



紙用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
C-350	Petroleum Wax 石油蜡	White Emulsion 白色乳液	40±1	3500±500	4~6	-	Water Repellent Agent, Used for Paper Internal Sizing and Surface Coating 紙張撥水劑, 廣泛應用於紙張內部上膠與表面塗佈	Acid Stable, Can be Blended with Rosin Soap for Application to Required Properties 具有良好酸安定性, 可與松香系上膠劑併用以調節所需求之物性
C-300	Petroleum Resin 石油樹脂	White Emulsion 白色乳液	30±1	<100	11.5~12.5	-	Water Repellent Agent 紙張撥水劑	Good Heat Resistance and Anti-slip 耐高溫, 不滑性
AM-200	Acrylic Resin 壓克力樹脂	White Emulsion 白色乳液	40±1	<100	4~5	35	Gloss Agent for Paper and Wallpaper Coating 紙張, 壁紙之亮光劑	Hard Film, Excellent Blocking & Water Resistance and Brightness 皮膜硬, 耐粘性、耐水、光澤性特優
MC-5	Styrene Acrylic Copolymer 苯乙烯壓克力共聚合樹脂	White Emulsion 白色乳液	50±1	<100	8~9	12	Binder for Art Paper and MC Coating 銅版紙, MC 塗佈用之膠料	Good Picking Property, Luster, Weather and Water Resistance 表面強度佳, 光澤、耐候、耐水性良好
MC-7	Styrene Acrylic Copolymer 苯乙烯壓克力共聚合樹脂	White Emulsion 白色乳液	45±1	3000±500	7~9	34	Binder for Art Paper and MC Coating 銅版紙, MC 塗佈用之膠料	Hard Film, Good Picking Property, Luster, Weather and Water Resistance 皮膜硬, 光澤、耐候、耐水性良好
P-25	Vinyl Acetate Acrylic Copolymer 醋酸乙烯壓克力共聚合樹脂	White Emulsion 白色乳液	50±1	<100	2~4	5	Binder for Art Paper and MC Coating 銅版紙, MC 塗佈用之膠料	Good Picking Property, Smoothness, Whiteness and Heat Resistance 表面強度佳, 平滑度、白度、耐熱性良好
2NS	Vinyl Acetate Resin 醋酸乙烯樹脂	White Emulsion 白色乳液	50±1	2500±500	2~4	13	Used in Undercoating of DIAZO Photo-Sensitive Paper 用於 DIAZO 感光紙之底層塗佈	Excellent Silica Miscibility and Water Resistance 矽粉混合性、耐水性良好
PC-45-2	Styrene Acrylic Copolymer 苯乙烯壓克力共聚合樹脂	White Emulsion 白色乳液	45±1	3000±500	7~9	34	Coating for Speaker's Cone Paper 喇叭紙, 塗佈用之膠料	Hard Film, Good Picking Property, Luster, Weather and Water Resistance 皮膜硬, 光澤、耐候、耐水性良好