



LIQUID PHENOLIC RESIN

液態酚醛樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	GRAVITY 比重	SOLUBILITY 溶解性	MAIN USES 主要用途	SPECIAL FEATURES 特性
B-3	Phenolic Resin 酚醛樹脂	Brown Reddish Liquid 赤褐色	48-52	40-50	1.00-1.07	IPA 異丙醇	Dipping Application on textile or paper 纖維織品或紙張等含浸加工用。	Strong penetration, Excellent Properties of Molding, Heat and Wet Resistance 浸透力強，成型、耐熱性佳，並俱優良之抗溼性
B-65	Phenolic Resin 酚醛樹脂	Brown Reddish Liquid 赤褐色	61-65	100-130	1.10-1.17	IPA 異丙醇	Dipping Application on textile or paper 纖維織品或紙張等含浸加工用。	Strong penetration, Excellent Properties of Molding, Heat and Wet Resistance 浸透力強，成型、耐熱性佳，並俱優良之抗溼性
PF-155N	Phenolic Resin 酚醛樹脂	Dark Brown Liquid 暗褐色	48-53	20-50	0.90-1.03	Methanol 甲醇	Dipping Application on textile or paper 纖維織品或紙張等含浸加工用。	Strong penetration, Excellent Properties of Molding, Heat and Wet Resistance 浸透力強，成型、耐熱性佳，並俱優良之抗溼性
BRL-111B	Phenolic Resin 酚醛樹脂	Brown Reddish Liquid 赤褐色	45-55	35-55	1.14-1.16	Water 水	Fastening of Rock Wool and Glass Fiber 岩棉織品或玻璃纖維固著加工用。	Strong penetration, Excellent Properties of Molding, Heat and Wet Resistance 浸透力強，成型、耐熱性佳，並俱優良之抗溼性