



# ACRYLIC RESINS

## 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°C mPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-511	苯乙烯共聚合物 (Styrene copolymer)	2250-3250 60% in 甲基乙基酮 (60% in MEK)	<ul style="list-style-type: none"> <li>● 路線漆 (road paint)</li> <li>● 船舶漆 (marine paint)</li> <li>● 外部塗料 (exterior coating)</li> <li>● 重型、金屬漆 (heavy duty and metal paint)</li> </ul>	<ul style="list-style-type: none"> <li>● 硬度佳 (good hardness)</li> <li>● 透明、耐彎曲性 (clear and flexible)</li> <li>● 高固型份 (high solids soluble)</li> <li>● 室外耐久性佳 (outdoor durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類 (aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-514	苯乙烯共聚合物 (Styrene copolymer)	2500-3500 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 水泥漆 (concrete paints)</li> <li>● 路線漆 (road paint)</li> <li>● 塑膠塗料 (plastic coatings)</li> </ul>	<ul style="list-style-type: none"> <li>● 耐化學性佳 (chemical resistant)</li> <li>● 對瀝青、混凝土時有良好之特性 (good properties on asphalt and concrete)</li> <li>● 耐久且硬 (durable and hard)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類 (aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-515	甲基丙烯酸異丁酯 均聚物 (IBMA homo polymer)	1000-1500 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 噴霧劑 (aerosols)</li> <li>● 墨水 (inks)</li> <li>● OPV's</li> </ul>	<ul style="list-style-type: none"> <li>● 韌性的膜 (flexible films)</li> <li>● 與底漆有高相容性 (high tolerant with pigments)</li> <li>● 低氣味 (low odour)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類 (aromatics)</li> <li>● 由石油溶劑、酮類 及芳香族類等混合 而成 (=mixture)</li> </ul>
AR-517	苯乙烯共聚合物 (Styrene copolymer)	450-650 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 路線漆 (road paint)</li> <li>● 船舶漆 (marine paint)</li> <li>● 水泥漆 (concrete paints)</li> <li>● 牆壁漆 (wall paints)</li> </ul>	<ul style="list-style-type: none"> <li>● 耐候佳佳 (good hardness)</li> <li>● 高光澤性 (high gloss)</li> <li>● 耐化學性佳 (chemical resistant)</li> <li>● 硬度佳 (good hardness)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類 (aromatics)</li> <li>● 酯類 (esters)</li> <li>● 石油溶劑 (white spirit)</li> </ul>
AR-518	苯乙烯共聚合物 (Styrene copolymer)	300-500 30% in 醋酸乙酯 (30% in EAc)	<ul style="list-style-type: none"> <li>● 鋁之表面塗層及底漆 (top coats and primers for aluminum)</li> <li>● 墨水 (inks)</li> </ul>	<ul style="list-style-type: none"> <li>● 高光澤性 (high gloss)</li> <li>● 極佳之耐化學性 (good chemical resistant)</li> <li>● 極佳之耐熱性 (good heat resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類 (aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-523	甲基丙烯酸丁酯 共聚合物 (BMA copolymer)	130-190 30% in 醋酸乙酯 (30% in EAc)	<ul style="list-style-type: none"> <li>● 陶磁 (ceramics)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 包裝油墨 (packaging inks)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 鋁熱封亮漆 (aluminum heat seal lacquers)</li> </ul>	<ul style="list-style-type: none"> <li>● 極佳之相容性 (very good compatible)</li> <li>● 低氣味 (low odour)</li> <li>● 耐水性佳 (water resistant)</li> <li>● 韌性的膜 (flexible films)</li> <li>● 室外耐久性佳 (outdoor durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類 (aromatics)</li> <li>● 酯類 (esters)</li> </ul>



# ACRYLIC RESINS

## 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°C mPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-531	甲基丙烯酸丁酯 共聚合物 (BMA copolymer)	100-300 30% in 甲苯 (30% in Toluene)	<ul style="list-style-type: none"> <li>● 陶磁與噴霧劑 (ceramics and aerosols)</li> <li>● 塑膠塗料 (packaging inks)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 強化醇酸塗料 (upgrading of alkyd paints)</li> <li>● 木條地板擦亮劑 (parquet polishes)</li> </ul>	<ul style="list-style-type: none"> <li>● 通過相對硬度 (though and relative hard)</li> <li>● 高光澤性 (high gloss)</li> <li>● 與底漆有高相容性 (high tolerant with pigments)</li> <li>● 極佳之耐化學性 (good heat resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-536	甲基丙烯酸丁酯 共聚合物 (BMA copolymer)	30-100 30% in 甲基乙基酮/醋酸乙酯 (30% in MEK/EAc)	<ul style="list-style-type: none"> <li>● 陶磁 (ceramics)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 傳輸亮漆(transfer lacquers)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 鋁熱封亮漆 (aluminum heat seal lacquers)</li> </ul>	<ul style="list-style-type: none"> <li>● 光澤性佳 (good gloss)</li> <li>● 與許多黏合劑相容性佳 (compatible with many binders)</li> <li>● 韌性的膜 (flexible films)</li> <li>● 優異的耐水性及耐生產性 (excellent water and product resistance)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-539	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚合物 (BMA/MMA copolymer)	200-400 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 船舶漆 (marine paint)</li> <li>● 噴霧劑 (aerosols)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 金屬塗料 (metal coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 易溶解 (easy solubility)</li> <li>● 極佳之耐化學性 (good chemical resistant)</li> <li>● 室外耐久性佳(outdoor durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-541	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚合物 (BMA/MMA copolymer)	2500-3500 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 金屬塗料 (metal coating)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 油墨 (inks)</li> <li>● 鋁亮漆(aluminum lacquers)</li> </ul>	<ul style="list-style-type: none"> <li>● 色彩持久 (colour retention)</li> <li>● 易溶解 (easy solubility)</li> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> <li>● 耐熱性佳 (good heat resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-543	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚合物 (BMA/MMA copolymer)	800-1300 30% in 二甲苯 (30% in Xylene)	<ul style="list-style-type: none"> <li>● 水泥漆 (concrete paints)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 木器塗料 (wood coating)</li> <li>● 金屬底漆塗料 (primed metal coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 極佳之耐化學性(good chemical resistant)</li> <li>● 室外耐久性佳 (outdoor durability)</li> <li>● 高光澤性 (high gloss)</li> <li>● 相容性佳 (very compatible)</li> <li>● 耐磨擦性佳 (abrasion resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>



# ACRYLIC RESINS

## 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°C mPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-544	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚物 (BMA/MMA copolymer)	300-450 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 船舶及金屬漆 (marine and metal paint)</li> <li>● 汽車修補漆 (car refinishing paint)</li> <li>● 路線漆與水泥漆 (road paint and concrete paints)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 塑料及木器塗料 (plastic and wood coatings)</li> </ul>	<ul style="list-style-type: none"> <li>● 極佳之耐熱性(good heat resistant)</li> <li>● 寬廣的相容性(wide compatibility)</li> <li>● 硬、堅韌、抗壓 (hard, tough, resistant)</li> <li>● 乾燥速度快、易溶解 (fast drying / easy solibility)</li> <li>● 室外耐久性佳 (outdoor durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-547	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚物 (BMA/MMA copolymer)	20-100 25% in 甲基乙基酮 (25% in MEK)	<ul style="list-style-type: none"> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 木器塗料 (wood coating)</li> <li>● 印刷油墨 (printing inks)</li> </ul>	<ul style="list-style-type: none"> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 乾燥速度快、低氣味 (fast drying / low odour)</li> <li>● 耐候性佳 (weather resistant)</li> <li>● 耐彎曲性及堅韌性 (outdoor durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-548	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚物 (BMA/MMA copolymer)	50-100 25% in 甲基乙基酮 (25% in MEK)	<ul style="list-style-type: none"> <li>● 印刷油墨 (printing inks)</li> <li>● 塑料及乙烯基塗料 (plastic and vinyl coatings)</li> <li>● PVC 飾潤 (PVC finishing)</li> </ul>	<ul style="list-style-type: none"> <li>● 極佳之耐化學性 (good chemical resistant)</li> <li>● 硬、堅韌、抗壓 (hard, tough, resistant)</li> <li>● 低氣味 (low odour)</li> <li>● 耐可塑劑(plasticizer resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-551	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚物 (BMA/MMA copolymer)	350-550 40% in 醋酸乙酯 (40% in EAc)	<ul style="list-style-type: none"> <li>● 陶磁傳輸亮漆 (ceramics transfer lacquers)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 金屬塗料 (metal coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 透明、堅韌、耐彎曲 (clear, tough, flexible)</li> <li>● 低氣味(low odour)</li> <li>● 易溶解 (easy solubility)</li> <li>● 極佳之耐熱性 (good heatresistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-552	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚物 (BMA/MMA copolymer)	800-1000 35% in 甲苯/甲基乙基酮 (35% in Toluene/MEK)	<ul style="list-style-type: none"> <li>● 印刷油墨 (printing inks)</li> <li>● 塑料及金屬塗料 (plastic and metal coatings)</li> <li>● 汽車修補漆 (car refinishing paint)</li> </ul>	<ul style="list-style-type: none"> <li>● 耐化學性佳 (chemical resistant)</li> <li>● 溶解性佳、堅韌、耐彎曲性 (good soluble, tough,flexible)</li> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>



# ACRYLIC RESINS

## 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°C mPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-554	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚合物 (BMA/MMA copolymer)	250-400 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 船舶及金屬漆 (marine and metal paint)</li> <li>● 汽車修補漆 (car refinishing paint)</li> <li>● 印刷及網版油墨 (printing and screen inks)</li> <li>● 噴霧劑 (aerosols)</li> <li>● 塑膠塗料、底漆 (plastic coatings, primer)</li> </ul>	<ul style="list-style-type: none"> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 硬、堅韌、抗壓 (hard, tough, resistant)</li> <li>● 韌性的膜 (flexible films)</li> <li>● 與底漆有高相容性 (high pigments soluble)</li> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-556	甲基丙烯酸丁酯/ 甲基丙烯酸甲酯 共聚合物 (BMA/MMA copolymer)	350-550 35% in 醋酸乙酯 (35% in EAc)	<ul style="list-style-type: none"> <li>● 水泥漆 (concrete paints)</li> <li>● 印刷油墨 (printing inks)</li> </ul>	<ul style="list-style-type: none"> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> <li>● 硬、堅韌、抗壓 (hard, tough, resistant)</li> <li>● 耐可塑劑 (plasticizer resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-560	丙烯酸乙酯/甲基丙 烯酸甲酯共聚合物 (EA/MMA copolymer)	450-650 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 印刷油墨 (printing inks)</li> <li>● 船舶及金屬漆 (marine and metal paint)</li> <li>● 塑膠塗料(plastic coatings)</li> </ul>	<ul style="list-style-type: none"> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 耐可塑劑 (plasticizer resistant)</li> <li>● 軟、耐彎曲 (soft and flexible)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-565	丙烯酸乙酯/甲基丙 烯酸甲酯共聚合物 (EA/MMA copolymer)	100-200 25% in 氨水/水 (25% in Ammonia/Water)	<ul style="list-style-type: none"> <li>● 切斷接著、底漆(road paint)</li> <li>● 顏料調配 (plastic coatings)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 鋁上塗料 (coatings on aluminum)</li> </ul>	<ul style="list-style-type: none"> <li>● 乾燥速度快 (fast drying)</li> <li>● 與架橋劑相容 (cross-linking compatibility)</li> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 低氣味、可印刷 (low odour, printable)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-568	丙烯酸乙酯/甲基丙 烯酸甲酯共聚合物 (EA/MMA copolymer)	100-300 30% in 乙醇 (30% in Ethanol)	<ul style="list-style-type: none"> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 油墨及過量印刷漆 (inks and overprint varnishes)</li> </ul>	<ul style="list-style-type: none"> <li>● 與醇類有良好之溶解性 (good alcohol soluble)</li> <li>● 低氣味(low odour)</li> <li>● 耐彎曲性 (flexible)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>



# ACRYLIC RESINS

## 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°C mPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-596	丙烯酸乙酯/甲基丙烯酸乙酯共聚合物 (EA/EMA copolymer)	125-225 30% in 乙醇/水 (30% in Ethanol/Water)	<ul style="list-style-type: none"> <li>● 印刷油墨 (printing inks)</li> <li>● 塑膠塗料(plastic coatings)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 熱封膜塗料 (heat sealable film coatings)</li> <li>● 金屬塗料 (metal coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 乾燥速度快 (fast drying)</li> <li>● 低氣味 (low odour)</li> <li>● 透明、堅韌、耐彎曲 (clear, tough, flexible)</li> <li>● 能覆蓋之塗料 (overcoatable)</li> <li>● 優異之接著性(excellent adhesion)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-592	甲基丙烯酸乙酯均聚物 (EMA homo polymer)	500-800 30% in 乙醇/水 (30% in Ethanol/Water)	<ul style="list-style-type: none"> <li>● 顏料調配 (plastic coatings)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 印刷油墨 (printing inks)</li> </ul>	<ul style="list-style-type: none"> <li>● 乾燥速度快、低氣味 (fast drying, low odour)</li> <li>● 良好之耐熱塑性 (good thermo resistant)</li> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> <li>● 極佳之耐化學性 (good abrasion resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-500	甲基丙烯酸異丁酯共聚合物 (IBMA copolymer)	20-100 30% in 甲苯 (30% in Toluene)	<ul style="list-style-type: none"> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 調色劑樹脂 (toner resin)</li> <li>● 水泥漆、牆壁漆 (concrete paints, wall paints)</li> </ul>	<ul style="list-style-type: none"> <li>● 脂肪族溶劑 (solvent in aliphatic solvent)</li> <li>● 耐候性佳、低氣味 (outdoor durability, low odour)</li> <li>● 抗結塊、硬度佳 (anti-blocking /good hardness)</li> </ul>	<ul style="list-style-type: none"> <li>● 許多溶劑 (many solvents)</li> </ul>
AR-570	甲基丙烯酸異丁酯共聚合物 (IBMA copolymer)	350 30% in 石油溶劑 (30% in White Spirit)	<ul style="list-style-type: none"> <li>● 木器及木條之磨光 (polish for wood and parquet)</li> <li>● 紙張塗料 (paper coating)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 木器塗料 (wood coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 優異之光澤硬膜 (excellent hard glossy films)</li> <li>● 優異之流動性及水平 (excellent flow and leveling)</li> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 耐久性佳 (durable)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-572	甲基丙烯酸異丁酯共聚合物 (IBMA copolymer)	2250 30% in 石油溶劑 (30% in White Spirit)	<ul style="list-style-type: none"> <li>● 噴霧劑 (aerosols)</li> <li>● 凸版及凹版印刷油墨 (flexo and gravure printing inks)</li> <li>● 塑膠及紙張塗料 (plastic and paper coatings)</li> <li>● 鋁上塗料 (coatings on aluminum)</li> </ul>	<ul style="list-style-type: none"> <li>● 透明、堅韌、硬 (clear, tough, hard)</li> <li>● 低氣味 (low odour)</li> <li>● 極佳之耐熱性 (good heat resistant)</li> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>



# ACRYLIC RESINS

## 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°CmPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-573	甲基丙烯酸異丁酯 共聚合物 (IBMA copolymer)	20-100 30% in 甲苯 (30% in Toluene)	<ul style="list-style-type: none"> <li>● 噴霧劑 (aerosols)</li> <li>● 塑膠與及醇酸塗料 (plastic and alkyd coatings)</li> <li>● 凹版印刷油墨 (gravure printing inks)</li> </ul>	<ul style="list-style-type: none"> <li>● 乾燥速度快、易溶解 (fast drying, easy solibility)</li> <li>● 透明、堅韌、耐彎曲 (clear, tough, flexible)</li> <li>● 接著性及耐久性佳 (good adhesion and durability)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-578	甲基丙烯酸異丁酯 均聚物 (IBMA homo polymer)	1000-2000 40% in 甲苯 (40% in Toluene)	<ul style="list-style-type: none"> <li>● 噴霧劑 (aerosols)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 油墨及過量印刷漆 (inks and overprint varnishes)</li> <li>● 路線及建築漆 (road and construction paints)</li> <li>● 木器塗料 (wood coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 室外耐久性佳 (outdoor durability)</li> <li>● 低氣味、耐熱性佳 (low odour / heat resistant)</li> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 易溶解 (easy solubility)</li> <li>● 透明、堅韌、硬 (clear, tough, hard)</li> </ul>	<ul style="list-style-type: none"> <li>● 醇類 (alcohols)</li> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-579	甲基丙烯酸異丁酯 共聚合物 (IBMA copolymer)	50-250 30% in 甲苯 (30% in Toluene)	<ul style="list-style-type: none"> <li>● 船舶及金屬漆 (marine and metal paint)</li> <li>● 路線漆與水泥漆 (road paint and concrete paints)</li> <li>● 牆壁漆及底漆 (wall paints and primer)</li> </ul>	<ul style="list-style-type: none"> <li>● 易溶解 (easy solubility)</li> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 室外耐久性佳 (outdoor durability)</li> <li>● 軟、耐彎曲 (soft and flexible)</li> </ul>	<ul style="list-style-type: none"> <li>● 許多溶劑 (many solvents)</li> </ul>
AR-591	甲基丙烯酸異丁酯 共聚合物 (IBMA copolymer)	500-700 40% in 乙酸丁酯/ 甲基戊酮 (30% in Butyl acetate/MIBK)	<ul style="list-style-type: none"> <li>● 耐彎曲性的基材 (flexible substrates)</li> <li>● 寬廣的相容性 (broad compatibility)</li> </ul>	<ul style="list-style-type: none"> <li>● 優異之接著性(excellent adhesion)</li> <li>● 寬廣的相容性(broad compatibility)</li> <li>● 易溶解 (easy solubility)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>
AR-582	甲基丙烯酸甲酯 均聚物 (MMA homo polymer)	20-50 25% in 甲基乙基酮 (25% in MEK)	<ul style="list-style-type: none"> <li>● 汽車修補漆 (car refinishing paint)</li> <li>● 塑膠塗料 (plastic coatings)</li> <li>● 印刷油墨 (printing inks)</li> <li>● 乙烯基塗料 (vinyl coating)</li> </ul>	<ul style="list-style-type: none"> <li>● 耐久性及硬度 (durable and hard)</li> <li>● 極佳之耐化學性 (good chemical resistant)</li> <li>● 耐可塑劑 (plasticizer resistant)</li> <li>● 良好之耐熱塑性 (good thermo resistant)</li> </ul>	<ul style="list-style-type: none"> <li>● 酮類 (ketones)</li> <li>● 芳香族類(aromatics)</li> <li>● 酯類 (esters)</li> </ul>



## ACRYLIC RESINS

### 壓克力(丙烯酸酯類)樹脂

品名 Product	主成分 Type	黏度 25°C mPa.s	主要用途 Application	特性 Properties	溶解性 Solubility
AR-587	甲基丙烯酸甲酯 均聚物 (MMA homo polymer)	400-750 30% in 甲基乙基酮 (30% in MEK)	<ul style="list-style-type: none"><li>● 汽車修補漆 (car refinishing paint)</li><li>● 塑膠塗料 (plastic coatings)</li><li>● 油墨 (inks)</li><li>● 乙烯基塗料 (vinyl coating)</li></ul>	<ul style="list-style-type: none"><li>● 耐久性及硬度 (durable and hard)</li><li>● 室外耐久性佳 (outdoor durability)</li><li>● 耐可塑劑 (plasticizer resistant)</li><li>● 耐熱性及耐濕性 (heat and moisture resistant)</li></ul>	<ul style="list-style-type: none"><li>● 酮類 (ketones)</li><li>● 芳香族類(aromatics)</li><li>● 酯類 (esters)</li></ul>
AR-584	甲基丙烯酸甲酯 共聚合物 (MMA copolymer)	250-350 30% in 甲苯/丁醇 (30% in Toluene/Butanol)	<ul style="list-style-type: none"><li>● 塑膠塗料 (plastic coatings)</li><li>● PVC 的金屬底漆 (metal primer for PVC)</li><li>● 油墨 (inks)</li></ul>	<ul style="list-style-type: none"><li>● 室外耐久性佳 (outdoor durability)</li><li>● 耐化學性及耐熱性 (chemical and heat resistant)</li><li>● 硬、耐彎曲 (hard and flexible)</li></ul>	<ul style="list-style-type: none"><li>● 酮類 (ketones)</li><li>● 芳香族類(aromatics)</li><li>● 酯類 (esters)</li></ul>
AR-589	甲基丙烯酸甲酯 共聚合物 (MMA copolymer)	400 30% in 甲苯 (30% in Toluene)	<ul style="list-style-type: none"><li>● 模型添加劑 (molding additive)</li><li>● 汽車內部 (road paint)</li><li>● 塑膠塗料 (plastic coatings)</li></ul>	<ul style="list-style-type: none"><li>● 極佳之耐化學性 (good chemical resistant)</li><li>● 耐熱性及耐濕性 (heat and moisture resistant)</li><li>● 耐可塑劑 (plasticizer resistant)</li></ul>	<ul style="list-style-type: none"><li>● 酮類 (ketones)</li><li>● 芳香族類(aromatics)</li><li>● 酯類 (esters)</li></ul>