



Aliphatic polyether polyol types

脂肪族聚醚多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2811	30	8	DMAC	< 300	17	800	200-250	<ul style="list-style-type: none"> ● 可曲折材質塗料 coat on flexible substrates ● 紙張及塑膠塗料 paper and plastic coating ● 聚氯乙烯塗料 PVC coating ● 皮革塗料 leather coating 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 soft and flexible ● 耐水性 water resistance ● 不黃變 non yellowing
L-2812	30	8	DMAC	< 300	50	550	350-400	<ul style="list-style-type: none"> ● 可曲折材質透料 coat on flexible substrates ● 皮革塗料 leather coating 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 soft and flexible ● 耐水性 water resistance ● 不黃變 non yellowing
L-2812M	35	8	NMP	< 500	76	450	470-520	<ul style="list-style-type: none"> ● 可曲折材質透料 coat on flexible substrates ● 皮革塗料 leather coating 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 soft and flexible ● 耐水性 water resistance ● 不黃變 non yellowing
L-2813	39	7.5	無溶劑 solvent free	115	55	550	210-260	<ul style="list-style-type: none"> ● 可剝離金屬塗料 peelable metal coating ● 印刷油墨及玻璃纖維上漿 printing ink and glass fiber ● 地板塗料 flooring coating ● 紙張及紡織品塗料 paper and textile coating 	<ul style="list-style-type: none"> ● 韌性佳 tough ● 無溶劑 solvent free ● 與丙烯酸乳液相容良好 compatible with acrylic emulsion
L-2815	39	7.5	無溶劑 solvent free	115	55	550	210-260	<ul style="list-style-type: none"> ● 可剝離金屬塗料 peelable metal coating ● 印刷油墨及玻璃纖維上漿 glass fiber sizing ● 皮革塗料 leather coating ● 紙張及紡織品塗料 paper and textile coating 	<ul style="list-style-type: none"> ● 韌性佳 tough ● 無溶劑 solvent free ● 與丙烯酸乳液相容良好 compatible with acrylic emulsion ● L-2813 不含乳化劑 emulsifier free version of L-2813



Aliphatic polyether polyol types

脂肪族聚醚多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2842	34	8.3	無溶劑 solvent free	95	66	600	200-250	<ul style="list-style-type: none"> ● 印刷油墨 printing ink ● 紙張及紡織品塗料 paper and textile coating ● 地板塗料 floor coating 	<ul style="list-style-type: none"> ● 與耐曲折材質接著性良好 good adhesion on flexible substrates ● 耐溶劑性 good solvent resistance
L-2851	34	7.8	NMP	325	145	350	330-380	<ul style="list-style-type: none"> ● 水泥塗料 concrete coating / wall paint ● 塑膠塗料 plastic coating ● 金屬塗料 metal coating ● 底塗處理劑 primer 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 tough and flexible ● 耐化學及耐磨性 chemical and abrasion resistance ● 良好接著性 good adhesion ● 高透明性及耐曲折性 high transparent & flexible ● 與塑膠接著性良好 good adhesion on many plastics ● 可架橋性 crosslinkable
L-2855	28	8.8	無溶劑 solvent free	30	71	270	175	<ul style="list-style-type: none"> ● 併木板及軟質木地板塗料 parquet & cork floor coating ● 抗塗鴉塗料 anti-graffiti-coating ● 水泥塗料 concrete coating / wall paint ● 金屬及塑膠塗料 metal and plastic coating 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 tough and flexible ● 耐化學性 chemical resistance ● 耐磨擦性 abrasion resistance ● 接著性良好 good adhesion
L-2857	34	7.6	NMP	275	128	350	350-400	<ul style="list-style-type: none"> ● 併木板及軟質木地板塗料 parquet & cork floor coating ● 抗塗鴉塗料 anti-graffiti-coating ● 水泥塗料 concrete coating / wall paint ● 金屬及塑膠塗料 metal and plastic coating 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 tough and flexible ● 耐化學性 chemical resistance ● 耐磨擦性 abrasion resistance ● 接著性良好 good adhesion



Aliphatic polyether polyol types

脂肪族聚醚多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2869	39	7.4	無溶劑 solvent free	100	50-60	550	220-270	<ul style="list-style-type: none"> ● 可剝離金屬塗料 peelable metal coating ● 印刷油墨及玻璃纖維上漿 printing ink and glass fiber ● 地板、紙張及紡織品塗料 floor,paper and textile coating 	<ul style="list-style-type: none"> ● 韌性佳 tough ● 無溶劑 solvent free ● 與丙烯酸乳液相容良好 compatable with acrylic emulsion
L-2872	33	8.5	無溶劑 solvent free	130				<ul style="list-style-type: none"> ● 底塗處理劑 primer 	<ul style="list-style-type: none"> ● 高透明性及可曲折性 high transparant and flexible ● 與塑膠接著性良好 good adhesion on many plastics good solvent resistance
L-2881	35	8.2	無溶劑 solvent free	400				<ul style="list-style-type: none"> ● 接著劑 adhesive 	<ul style="list-style-type: none"> ● 耐熱性 heat resistance ● 接著性良好 good adhesion ● 透明及安定性佳 clear and stable
L-2883	30	9.5	NMP	175				<ul style="list-style-type: none"> ● 紙張及塑膠塗料 paper and plastic coating ● 水泥及金屬塗料 concrete and metal coating ● 木材及併木地板透明塗料 wood/parquet lacquer/coating 	<ul style="list-style-type: none"> ● 硬質及耐曲折性 hard and flexible ● 耐磨擦及耐化學性 abrasion and chemical resistance ● 接著性良好 good adhesion ● 芳香族聚醚多元醇型 aromatic polyether polyol type



Aliphatic polyether polyol types

脂肪族聚醚多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100%modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2887	40	7.8	無溶劑 solvent free	200	33	650	160-200	<ul style="list-style-type: none"> ● 耐曲折塗料 flexible coating ● 軟木地板透明塗料 cork floor lacquer ● 木材及併木地板透明塗料 wood/parquet lacquer/coating 	<ul style="list-style-type: none"> ● 柔軟耐曲折性 soft and very flexible ● 耐紫外線 UV resistance ● 耐磨擦性 abresion resistance ● L-2889 不含乳化劑 emulsifer free version of L-2889
L-2889	40	7.8	無溶劑 solvent free	200	33	650	160-200	<ul style="list-style-type: none"> ● 耐曲折塗料 flexible coating ● 皮革頂塗 leather topcoat 	<ul style="list-style-type: none"> ● 耐紫外線 UV resistance ● 耐磨擦性 abresion resistance ● L-2889 不含乳化劑 emulsifer free version of L-2889
L-2891	35	8	無溶劑 solvent free	200				<ul style="list-style-type: none"> ● 接著劑 Adhesive leather coating 	<ul style="list-style-type: none"> ● 接著性良好 good adhesion ● 韌性及耐曲折性 tough and flexible



Aliphatic polyester polyol types

脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2908	33.5	7.8	NMP	275	183	250	270-320	<ul style="list-style-type: none"> ● 網版及蝕版油墨 screen & gravure inks ● 水泥及金屬塗料 concrete & metal coating ● 聚氯乙烯塗料 vinyl top coat ● 木材及塑膠塗料 wood and plastic coat ● 織品塗料 textured coat 	<ul style="list-style-type: none"> ● 硬質及耐曲折性 hard, flexible and durable ● 耐化學性 chemical resistance ● 耐水、耐溼氣及耐紫外線 water, humidity, UV resistance ● 耐磨擦性 bresion resistance ● L-2909 不含消泡劑 defoamer free version of L-2909
L-2909	33.5	7.8	NMP	275	183	250	270-320	<ul style="list-style-type: none"> ● 網版及蝕版油墨 screen & gravure inks ● 水泥及金屬塗料 concrete & metal coating ● 聚氯乙烯塗料 vinyl top coat ● 木材及塑膠塗料 wood and plastic coat ● 織品塗料 textured coat 	<ul style="list-style-type: none"> ● 硬質及耐曲折性 hard, flexible and durable ● 耐化學性 chemical resistance ● 耐水、耐溼氣及耐紫外線 water, humidity, UV resistance ● 耐磨擦性 bresion resistance ● 耐水、耐溼氣及耐紫外線 water, humidity, UV resistance
L-2911	30.0	8	DMAC	< 300	32	500	200-250	<ul style="list-style-type: none"> ● PVC 地板印刷油墨 Printing ink on PVC flooring ● 紙張及塑膠塗料 paper, leather and plastic coating ● 木材及併木地板透明塗料 wood / parquet acquer/coating 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 soft and flexible ● 耐磨擦性 abresion resistance ● 不黃變 non yellowing
L-2916	39.5	8.5	NMP	350	181	250	300-350	<ul style="list-style-type: none"> ● 金屬及修補塗料 metal finishing repair coating ● 地板蠟及木材底塗處理劑 floor polish and wood primer ● 紙張及塑膠塗料 paper and plastic coating ● 木材及併木地板透明塗料 wood and paquet coating ● 皺紋塗料 textured coat 	<ul style="list-style-type: none"> ● 硬質及耐化學性 hard and chemical resistance ● 耐濕氣及耐磨擦性 humidity and abrasion resistance ● 耐黑鞋跟痕跡 BHMR resistance ● 與多種材質接著性良好 adhesion on many substrates ● 用途廣泛 broad range of application



Aliphatic polyester polyol types

脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2917	34.0	8.4	NMP	90	47	500	200-250	<ul style="list-style-type: none"> ● 印刷油墨 printing inks ● 塑膠、皮革及水泥塗料 plastic, leather, concrete coating ● 金屬、木材及紙張塗料 metal, wood, paper coating ● 併板透明塗料 parquet lacquer 	<ul style="list-style-type: none"> ● 耐曲折及耐磨性 flexible and abrasion resistance ● 與塑膠接著性良好 excellent adhesive to plastic ● 耐化學性 chemical resistance ● 與丙烯酸乳液相容良好 compatible with acrylic emulsion
L-2918	40.0	8	NMP	300	181	250	300-350	<ul style="list-style-type: none"> ● 薄板接著劑 laminating adhesive ● 木材及併木地板透明塗料 wood and parquet lacquer ● 金屬及塑膠塗料 metal and plastic coating 	<ul style="list-style-type: none"> ● 硬質及耐化學性 hard and chemical resistance ● 耐濕氣及耐磨擦性 humidity and abrasion resistance ● 耐黑鞋跟痕跡 BHMR resistance ● 與多種材質接著性良好 adhesion on many substrates ● L-2916 不含乳化劑 emulsifier free version of L-2916
L-2919	39.0	8	NMP	225				<ul style="list-style-type: none"> ● 金屬及修補塗料 metal finishing repair coating ● 地板臘及木材底塗處理劑 floor polish and wood primer ● 紙張及塑膠塗料 paper and plastic coating ● 木材及併木地板透明塗料 wood and parquet coating ● 織品塗料 textured coat 	<ul style="list-style-type: none"> ● 硬質及耐化學性 hard and chemical resistance ● 耐濕氣及耐磨擦性 humidity and abrasion resistance ● 耐黑鞋跟痕跡 BHMR resistance ● 與多種材質接著性良好 adhesion on many substrates ● 用途廣泛 broad range of application



Aliphatic polyester polyol types

脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2933	38.2	8.6	無溶劑 solvent free	250	11	700	60-80	● 薄板接著劑 laminating adhesive	● 耐熱性 good heat resistance ● 透明及耐光性 clear and light stable ● 與多種材質接著性良好 excellent adhesion to many substrates
L-2939	34.5	8.6	無溶劑 solvent free	90				● 金屬塗料 metal coating	● 韌性及耐曲折性 tough and flexible ● 耐化學性 chemical and water resistance
L-2946	32	8.3	NMP	130	165	300	270-310	● 印刷油墨及玻璃塗料 printing ink and glass coating ● 水泥塗料 concrete coating ● 木材及併木地板透明塗料 wood and parquet lacquer	● 與耐曲折材質接著性良好 good adhesion on flexible substrates ● 耐溶劑性及抗粘性 good solvent and blocking resistance ● 硬質及耐曲折性 hard and flexible
L-2955	38.2	8.1	無溶劑 solvent free	150	11	700	65-85	● 接著劑 adhesive	● 耐曲折性 Flexible ● 耐濕氣性 humidity resistance ● 接著性良好 good adhesion
L-2976	33.8	7.7	NMP	400	180	250	270-320	● 網版印刷油墨 screen ink ● 金屬及塑膠塗料 metal and plastic coating ● 木材及併木地板透明塗料 wood and parquet lacquer	● 硬質及快速乾燥 hard and fast drying ● 耐化學性 chemical resistance ● 耐磨擦性 abrasion resistance



Aliphatic polyester polyol types

脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (% w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-2980	34	8.4	NMP	125				<ul style="list-style-type: none"> ● 工業木材塗料 industrial wood coating 	<ul style="list-style-type: none"> ● 耐曲折性、但耐化學性差 flexible, poor chemical resistance ● 耐濕氣性及耐磨擦性 humidity and abrasion resistance ● L-2982 不含乳化劑 emulsifer free version of L-2982
L-2982	34	8.4	NMP	125				<ul style="list-style-type: none"> ● 印刷油墨 printing inks ● 金屬、水泥及塑膠塗料 metal, concrete and plastic coating ● 木材及併木地板透明塗料 wood and parquet lacquer 	<ul style="list-style-type: none"> ● 耐曲折性、但耐化學性差 flexible, poor chemical resistance ● 耐濕氣性 humidity resistance ● 耐磨擦性 abrasion resistance
L-2994	37.6	8.2	無溶劑 solvent free	150				<ul style="list-style-type: none"> ● 凸版及凹版印刷油墨 flexo and gravure inks ● 印刷油墨 printing inks 	<ul style="list-style-type: none"> ● 與塑膠材質接著性良好 excellent adhesion to plastic ● 耐曲折性特佳 very flexible
L-2991	39	8	NMP	100				<ul style="list-style-type: none"> ● 印刷油墨 printing inks ● 塑膠塗料 plastic coating ● 皮革塗料 leather coating ● 水泥塗料 concrete coating ● 木材及併木地板透明塗料 wood and parquet lacquer 	<ul style="list-style-type: none"> ● 韌性及耐曲折性 tough and flexible ● 與塑膠材質接著性良好 excellent adhesion to plastic ● 耐化學及耐磨性 chemical and abrasion resistance ● 與丙烯酸乳液相容良好 compatible with acrylic emulsion
L-2999	40	8.1	無溶劑 solvent free	60				<ul style="list-style-type: none"> ● 併木地板透明塗料 wood and parquet lacquer ● 軟質木材透明塗料 cork lacquer 	<ul style="list-style-type: none"> ● 中硬度、韌性及透明性佳 tough, medium hard and clear ● 耐濕氣及耐化學性 humidity and chemical resistance



Aliphatic polycarbonate polyol types

脂肪族聚碳酸多元醇型

ITEM NO. 製品編號	SOLID CONTENT (% w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100% modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-3021	39.5	8.1	NMP	275				<ul style="list-style-type: none"> ● PVC 地板頂塗 PVC flooring top coat ● 非 PVC 地板頂塗 non- PVC flooring top coat ● 結合丙烯酸乳液用於塑膠及木材塗料 plastic and wood coating in combination with acrylic emulsion 	<ul style="list-style-type: none"> ● 硬度及韌性佳 very hard and tough ● 耐水性及耐髒性 water and staining resistance ● 耐化學性 good chemical resistance ● 耐曲折性特佳 very flexible ● 耐磨擦性 abrasion resistance
L-3033	39.3	8.2	NMP	500				<ul style="list-style-type: none"> ● 工業用漆 industrial enamels ● 汽車底塗 automotive primer 	<ul style="list-style-type: none"> ● 機械性及皮膜特性佳 good mechanical and film properties ● 耐溶劑性 solvent resistance ● 曲折性 flexible
L-3042	35.4	7.9	NMP	100	53	230	151	<ul style="list-style-type: none"> ● PVC 地板頂塗及上光油 PVC flooring top coating ● 金屬及塑膠塗料 metal and plastic coating / primer ● 木材及柃木地板透明塗料 wood and parquet lacquer / coating ● 上光油 overprint varnishes ● 傢俱及紡織品塗料 furniture and texture coating 	<ul style="list-style-type: none"> ● 硬質、韌性佳 very hard and tough ● 耐曲折性特佳 very flexible ● 耐化學性及耐溶劑性 good chemical and solvent resistance ● 與塑膠材質接著性良好 good adhesion to plastics ● 耐水、耐溼氣及耐紫外線 water, humidity, UV resistance



Aliphatic polyester polycarbonate types

脂肪族聚碳酸多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100%modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-3050	34.7	8.0	NMP	90	80	170	163	<ul style="list-style-type: none">● PVC 地板頂塗 PVC top coat● 非 PVC 地板頂塗 non-PVC top coat● 金屬塗料 metal coating● 木材及併木地板透明塗料 wood and parquet acquer/coating	<ul style="list-style-type: none">● 硬質、韌性佳 very hard and tough● 耐曲折性特佳 very flexible● 耐化學性及耐溶劑性 good chemical and solvent resistance● 與塑膠材質接著性良好 good adhesion to plastics● 耐水、耐溼氣及耐紫外線 water, humidity, UV resistance



UV curable type

紫外線硬化型

ITEM NO. 製品編號	SOLID CONTENT (%w/w) 固型份	PH 酸鹼度 25°C	Cosolvent 共溶劑	VISCOSITY (25°C mPa.s) 粘度	100%modulus kg/cm2 100%抗張力	Elongation 伸長率	Tensile Strength 抗張力 kg/cm2	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-3410	39.8	8.0		200				<ul style="list-style-type: none">● PVC 及非 PVC 地板頂塗 PVC and non-PVC flooring● 傢俱塗料 furniture coating● 紙張及塑膠塗料 paper and plastic coating● 上光油及油墨 overprint varnishes and inks● 木材及併木地板透明塗料 wood/parquet lacquer/coating	<ul style="list-style-type: none">● 硬質及耐曲折性 hard and flexible● 耐磨擦性 abrasion resistance● 指觸乾燥後進行紫外線硬化 hand dry before UV curing● 耐化學性及耐污性 chemical and stain resistance



AQUEOUS POLYURETHANE/ ACRYLATES Aliphatic polyester polyol types

水性聚胺酯/丙烯酸樹脂

脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%) 固型份	PH 酸鹼度 25°C	M. F. T. (°C) 最低造膜溫度	VISCOSITY (25°C CPS) 粘度	Freeze/Thaw Stable 抗凍性	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-3926	35.0	8	34	<100	yes	<ul style="list-style-type: none"> ● 工業木材塗料 industrial wood coating ● 紙纖維板塗料 pigment board coating 	<ul style="list-style-type: none"> ● 耐水、耐化學及耐紫外線性 water, chemical and UV resistance ● 良好木材濕潤性 good wood wetting ● 磨沙性 sandability
L-3935	34.5	7.8	<15	100	yes	<ul style="list-style-type: none"> ● 工業木材塗料 industrial wood coating ● 併木板光油 parquet lacquer ● 水泥地板塗料 concrete floor coating ● 木材透明塗料 wood varnishes ● 金屬塗料 metal coating 	<ul style="list-style-type: none"> ● 韌性、柔軟及透明 tough, flexible and clear ● 高耐水及耐酒精性 high water and alcohol resistance ● 耐化學性及耐磨性 chemical and abrasion resistance ● 不黃變 non yellowing
L-3952	35.2	7.8	29	90	yes	<ul style="list-style-type: none"> ● 併木板光油(平光) parquet lacquer (flat) ● 油墨 inks ● 裝飾性塗料 decorative paint 	<ul style="list-style-type: none"> ● 優異耐化學性 excellent chemical resistance ● 優異耐黑鞋跟痕跡 excellent BHMR ● 不黃變 non yellowing
L-3958	35.0	8.0	xxxx	75	no	<ul style="list-style-type: none"> ● 可曲折材質透明塗料 clear coat on flexible substrates ● 軟木地板光油 cork floor lacquer 	<ul style="list-style-type: none"> ● 優異耐化學性 excellent chemical resistance ● 非常柔軟薄膜 very flexible film ● 不黃變性及低硬度 non yellowing and low hardness
L-3965	35.2	8.0	30	500	yes	<ul style="list-style-type: none"> ● 傢俱底漆及面漆 primer and top coat for furniture lacquer ● 工業木材塗料 industrial wood coating ● 併木板光油 parquet lacquer 	<ul style="list-style-type: none"> ● 優異木材濕潤性及流平性 excellent wood wetting and flow ● 耐刮性 scratch resistance ● 耐化學性及溶劑性 chemical and solvent resistance ● 光澤、透明性 glossy and transparent



水性聚胺酯/丙烯酸樹脂

脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%) 固型份	PH 酸鹼度 25°C	M. F. T. (°C) 最低造膜溫度	VISCOSITY (25°C CPS) 粘度	Freeze/Thaw Stable 抗凍性	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-3973	34.8	9.1	xxxx	100	yes	● 工業木材塗料 industrial wood coating	● 優異木材濕潤性及流平性 excellent wood wetting and flow ● 硬質、光澤、透明性 hard, glossy and transparent ● 耐化學性及耐刮性 chemical and scratch resistance ● 耐護手膏性 hand-cream resistance
L-3711	35.3	8.2	xxxx	100	yes	● 工業木材塗料 industrial wood coating	● 優異木材濕潤性及流平性 excellent wood wetting and flow ● 耐刮性 scratch resistance ● 耐化學性 chemical resistance ● 高透明性 high transparency
L-3722	33.3	8.8	45	<175	yes	● 工業木材塗料 industrial wood coating	● 良好濕潤性 good wood wetting ● 抗粘性 block resistance ● 耐化學性 chemical resistance ● 硬質 Hard ● 耐護手膏性 hand-cream resistance



AQUEOUS POLYURETHANE/ ACRYLATES Aliphatic polyester polyol types

水性聚胺酯/丙烯酸樹脂 脂肪族聚酯多元醇型

ITEM NO. 製品編號	SOLID CONTENT (%) 固型份	PH 酸鹼度 25°C	M. F. T. (°C) 最低造膜溫度	VISCOSITY (25°C CPS) 粘度	Freeze/Thaw Stable 抗凍性	MAIN USES 主要用途	SPECIAL FEATURES 特性
L-3728	38.2	8.0	xxxx	<80	yes	● 工業木材塗料 Industrial wood coating	● 優異木材濕潤性及流平性 excellent wood wetting and flow ● 耐刮性 scratch resistance ● 耐化學性及溶劑性 chemical and solvent resistance ● 高光澤性及透明性 glossy and transparent