



ACRYLIC RESIN FOR POWDER COATINGS

ITEM NO.	EPOXIDE EQUIVALENT WEIGHTS (g/epoxide eq.)	GARDNER COLOUR (maximum)	VISCOSITY (ICI cone and plate)	T _g (°C) (approximate)	CURING CONDITION (OBJECT TEMP.)	RATIO P.E. RESIN / ACRYLIC	SPECIAL FEATURE
FC-100	—	1	—	—	—	—	highly effective leveling agent. excellent weathering resistance and binder compatibility.
AG-500	500~570	2	350~600 (at 165°C)	65	10min / 200°C	75 / 25	one shot, exterior, adjustable low gloss system together with EL-8300. contamination Free.
AG-750	730~780	2	150~300 (at 200°C)	75	10min / 200°C	78.5 / 21.5	one shot, exterior, adjustable low gloss system together with EL-8300. contamination Free.
AG-800	780~850	2	180~230 (at 200°C)	73	10min / 200°C	77.5 / 22.5	one shot, exterior, adjustable low gloss system together with EL-8300. contamination Free.