



ADHESIVE RESINS

接著用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	Ti 觸變性	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
AC-260	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	60±2	110,000±20,000	3~5	3.1	4	For General Purpose and Wood Working 一般接著，木工用接著	High Concentration, Drying Speed and Excellent Bonding Strength 高固型份，乾燥速度快，接著力大
AC-260L	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	57±2	25,000±5,000	3~5	2.1	0	For General Purpose and Wood Working 一般接著，木工用接著	High Concentration, Drying Speed and Excellent Bonding Strength 高固型份，乾燥速度快，接著力大
AC-200	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	130,000±20,000	3~5	2.9	7	For General Purpose and Wood Working 一般接著，木工用，紡織品上膠劑	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-200N	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	120,000±20,000	3~5	3.3	10	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-220H	Acrylic Resin 壓克力樹脂	White Emulsion 白色乳膠	50±2	40,000±5,000	3~5	2.4	9	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-220	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	30,000±5,000	3~5	2.4	9	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-220S	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	8,000±2,000	3~5	1.6	9	Adhesive for Face Paper of Paper Tube Making and General Purpose 紙管面膠，一般接著	Drying Speed and Excellent Bonding Strength 乾燥速度快，接著力大
AC-220SE	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	4,000±1,000	3~5	1.6	9	Adhesive for Face Paper of Paper Tube Making and General Purpose 紙管面膠，一般接著	Drying Speed and Excellent Bonding Strength 乾燥速度快，接著力大
AC-220SE-1	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	4,000±1,000	3~5	1.1	9	For Paper Tube Making and General Purpose 紙管接著，一般接著	Drying Speed and Excellent Bonding Strength 乾燥速度快，接著力大
AC-220SE-2	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	50±2	2,500±500	3~5	1.1	9	For Paper Tube Making and General Purpose 紙管接著，一般接著	Drying Speed and Excellent Bonding Strength 乾燥速度快，接著力大
AC-220LK	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 淺灰色乳膠	48±2	25,000±3,800	3~5	2.7	9	For General Purpose and Good Water Resistant 一般接著，耐水性佳	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-245	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	45±2	120,000±20,000	3~5	3.3	10	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240G	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	180,000±20,000	3~5	4.1	7	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240H	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	130,000±20,000	3~5	3.2	7	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	85,000±15,000	3~5	3.5	7	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240L	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	45,000±7,000	3~5	2.5	7	For General Purpose and Wood Working 一般接著，木工用接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳



ADHESIVE RESINS

接著用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	Ti 觸變性	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
AC-240LL	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	35,000±5,000	3~5	2.1	7	For General Purpose and Wood Working 一般接著，木工用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240SH	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	9,000±1,000	3~5	1.4	9	For Paper Tube Making and General Purpose 紙管接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240S	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	4,000±1,000	3~5	1.4	9	For Paper Tube Making and General Purpose 紙管接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240SL	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	2,700±300	3~5	1.4	9	For Paper Tube Making and General Purpose 紙管接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240A	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	40±2	90,000±10,000	6~8	3.2	17	For General Purpose, Wood Working and Textile Sizing 一般接著，木工用，紡織品漿劑	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240N	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	42±2	6,000±1,000	3~5	2.0	7	For Paper Tube Making and General Purpose 紙管接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-240NL	Acrylic Resin 壓克力樹脂	White Emulsion 白色乳膠	39±2	3,500±5,000	3~5	2.4	7	For Paper Tube Making and General Purpose 紙管接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-235H	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	35±2	120,000 20000	3~5	4.1	6	For General Purpose and Wood Working 一般接著，木工用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-235	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	35±2	85,000±12,000	3~5	4.6	6	For General Purpose and Wood Working 一般接著，木工用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-235L	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	35±2	30,000±5,000	3~5	3.7	6	For General Purpose and Wood Working 一般接著，木工用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-235A	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	35±2	30,000±5,000	6~8	3.7	17	For General Purpose and Wood Working 一般接著，木工用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-230	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 淺灰色乳膠	30±2	90,000±10,000	3~5	4.0	0	For General Purpose and Wood Working 一般接著，木工用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-230L	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	30±2	30,000±5,000	3~5	3.3	0	For General Purpose and Wood Working 一般接著，小包裝用	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-230S	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	30±2	10,000±2,000	3~5	4.0	9	Adhesion for Paper and General Purpose 紙膠接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-230S-1	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	30±2	20,000±2,000	3~5	4.1	9	Adhesion for Paper and General Purpose 紙膠接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳
AC-200NL	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	49±2	45,000±6,500	3~5	4.1	9	Adhesion for Paper and General Purpose 紙膠接著，一般接著	Excellent Bonding Strength and Storage Stability 接著力大，儲存安定性佳



ADHESIVE RESINS

接著用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	Ti 觸變性	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
AC-200NL-1	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	49±2	55,000±1,000	3~5	2.4	9	Adhesion for Paper and General Purpose 紙張接著, 一般接著	Excellent Bonding Strength and Storage Stability 接著力大, 儲存安定性佳
AC-150	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	45±2	8,000±2,000	3~5	2.6	10	Adhesion for Coconut Fiber and Paper Tube Making 椰子棕上漿, 紙管接著	Excellent Bonding Strength and Storage Stability 接著力大, 儲存安定性佳
AC-145	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	45±2	45,000±9,000	3~5	3.7	17	Textile Sizing 紡織品上漿劑	Excellent Bonding Strength and Storage Stability 接著力大, 儲存安定性佳
AC-145H	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	45±2	90,000±10,000	3~5	3.7	17	Textile Sizing 紡織品上漿劑	Excellent Bonding Strength and Storage Stability 接著力大, 儲存安定性佳
AC-135N-3	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	36±2	5,000±2,000	3~5	2.5	9	For Paper Tube Making and General Purpose 紙管接著, 一般接著	Excellent Bonding Strength and Storage Stability 乾燥速度快, 接著力大
AC-135N-1	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	35±2	3,000±1,000	3~5	2.0	9	For Paper Tube Making and General Purpose 紙管接著, 一般接著	Excellent Bonding Strength and Storage Stability 乾燥速度快, 接著力大
AC-135S-1	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	36±2	4,000±1,000	3~5	3.4	9	For Paper Tube Making and General Purpose 紙管接著, 一般接著	Excellent Bonding Strength and Storage Stability 接著力大, 儲存安定性佳
AC-125	Polyvinyl Acetate 醋酸乙稀樹脂	White Emulsion 白色乳膠	25±2	100±20	3~5	1.1	12	Textile Sizing 紡織品上漿劑	Low Concentration, Drying Speed and Excellent Bonding Strength 低固型份, 乾燥速度快, 接著力大
AR-400	Vinyl Acetate Acrylic Copolymer 醋酸乙稀壓克力共聚樹脂	White Emulsion 白色乳膠	40±2	60,000±10,000	3~5	3.2	7	Adhesion of Aluminum Foil 鋁箔貼合	Excellent Bonding Strength and Storage Stability 乾燥速度快, 接著力大
PW-100L	Polyvinyl Alcohol 聚乙稀醇樹脂	White Emulsion 白色乳膠	13±2	10,000±3,000	5~7	1.2	10	Adhesion of Label 標籤貼合	Low Concentration, Drying Speed and Excellent Bonding Strength 低固型份, 乾燥速度快, 接著力大
AD-6800	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	55±2	55,000±5,000	4~6	4.1	0	Lamination of PVC Sheet and Plywood, Applicable in Particle Wood PVC 皮與合板之貼合膠料適用於縮合板	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強, 耐熱性良好
AD-6800L	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	55±2	35,000±10,000	4~6	3.4	0	Lamination of PVC Sheet and Plywood, Applicable in Multilayer Wood PVC 皮與合板之貼合膠料適用於積層板	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強, 耐熱性良好
AD-6600	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	51±2	80,000±15,000	4~6	3.5	0	Lamination of PVC Sheet and Plywood, Applicable in Particle Wood PVC 皮與合板之貼合膠料適用於縮合板	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強, 耐熱性良好
AD-4000	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	50±2	65,000±10,000	4~6	3.2	0	Lamination of PVC Sheet and Plywood, Applicable in Cabinet (Ex. Speaker Case) PVC 皮與合板之貼合膠料適用於木箱製品(如喇叭箱)	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強, 耐熱性良好



ADHESIVE RESINS

接著用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	Ti 觸變性	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
AD-4000L	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	50±2	14,000±3,000	4-6	3.9	0	Lamination of PVC Sheet and Plywood, Aluminum Foil and Paper PVC 皮與合板之貼合膠料，鋁箔與紙張之貼合膠料	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強而熱性良好
AD-2000H	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	47±2	60,000±12,000	4-6	3.4	0	Lamination of PVC Sheet and Plywood PVC 皮與合板之貼合膠料	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強而熱性良好
AD-2000	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	47±2	20,000±2,000	4-6	3.1	0	Lamination of PVC Sheet and Plywood PVC 皮與不織布紡織品之貼合膠料	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強而熱性良好
AD-1500	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	50±2	375±75	4-6	2.8	0	Adhesion for Cigarette Holder in High Speed Operation 高速煙支封口用膠	Good Mechanical Stability and Bonding Strength 機械操作性良好，接著力大，高速接著
AD-1050	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	51±2	1000±300	4-6	2.8	0	For Paper Tube Making and General Purpose 紙張接著，一般接著	Drying Speed and Excellent Bonding Strength 乾燥速度快，接著力大
AD-600T	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	60±2	4,000±1,000	4-6	2.8	0	Water Proof for Concrete 混凝土用防水劑	High Concentration, Good Concrete Miscibility and Water Proof 高固型份，與混凝土混合性良好，防水性佳
AD-550T	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	3,500±1,000	4-6	3.2	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好，防水性佳
AD-550K	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	4,750±750	4-6	3.2	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好，防水性佳
AD-550J	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	3,000±1,000	4-6	2.7	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好，防水性佳
AD-68T	Ethylene Vinyl Acetate Copolymer 乙稀-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	2,500±500	4-6	2.7	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好，防水性佳