



ADHESIVE RESINS

ITEM NO.	MAIN COMPONENT	FORM	SOLID CONTENT (%)	VISCOSITY (CPS)	PH	Ti	M. F. T. (°C)	MAIN USES	SPECIAL FEATURES
AD-6800	Ethylene Vinyl Acetate Copolymer	White Emulsion	55±2	55,000±5,000	4~6	4.1	0	Lamination of PVC Sheet and Plywood, Applicable in Particle Wood	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-6800L	Ethylene Vinyl Acetate Copolymer	White Emulsion	55±2	25,000±5,000	4~6	3.4	0	Lamination of PVC Sheet and Plywood, Applicable in Multilayer Wood	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-6600	Ethylene Vinyl Acetate Copolymer	White Emulsion	51±2	80,000±15,000	4~6	3.5	0	Lamination of PVC Sheet and Plywood, Applicable in Particle Wood	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-4000	Ethylene Vinyl Acetate Copolymer	White Emulsion	50±2	65,000±10,000	4~6	3.2	0	Lamination of PVC Sheet and Plywood, Applicable in Cabinet (Ex. Speaker Case)	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-4000L	Ethylene Vinyl Acetate Copolymer	White Emulsion	50±2	14,000±3,000	4~6	3.9	0	Lamination of PVC Sheet and Plywood, Aluminum Foil and Paper	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-2000H	Ethylene Vinyl Acetate Copolymer	White Emulsion	47±2	60,000±12,000	4~6	3.4	0	Lamination of PVC Sheet and Plywood	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-2000	Ethylene Vinyl Acetate Copolymer	White Emulsion	47±2	20,000±2,000	4~6	3.1	0	Lamination of PVC Sheet and Plywood	Excellent Bonding Strength with PVC Sheet and good Heat Resistance
AD-1500	Ethylene Vinyl Acetate Copolymer	Milky White	50±2	375±75	4~6	2.8	0	Adhesion for Cigarette Holder in High Speed Operation	Good Mechanical Stability and Bonding Strength
AD-1050	Ethylene Vinyl Acetate Copolymer	Milky White	51±2	1000±300	4~6	2.8	0	For Paper Tube Making and General Purpose	Drying Seed and Excellent Bonding Strength
AD-600T	Ethylene Vinyl Acetate Copolymer	Milky White	60±2	4,000±1,000	4~6	2.8	0	Water Proof for Concrete	High Concentration , Good Concrete Miscibility and Water Proof
AD-550T	Ethylene Vinyl Acetate Copolymer	Milky White	55±2	3,500±1,000	4~6	3.2	0	Water Proof for Concrete	Good Concrete Miscibility and Water Proof
AD-550K	Ethylene Vinyl Acetate Copolymer	Milky White	55±2	4,750±750	4~6	3.2	0	Water Proof for Concrete	Good Concrete Miscibility and Water Proof
AD-550J	Ethylene Vinyl Acetate Copolymer	Milky White	55±2	3,000±1,000	4~6	2.7	0	Water Proof for Concrete	Good Concrete Miscibility and Water Proof
AD-68T	Ethylene Vinyl Acetate Copolymer	Milky White	55±2	2,500±500	4~6	2.7	0	Water Proof for Concrete	Good Concrete Miscibility and Water Proof