



## ADHESIVE RESINS

### 接著用樹脂

ITEM NO. 製品編號	MAIN COMPONENT 主成分	FORM 外觀	SOLID CONTENT (%) 固型份	VISCOSITY (CPS) 粘度	PH 酸鹼度	Ti 觸變性	M. F. T. (°C) 最低造膜溫度	MAIN USES 主要用途	SPECIAL FEATURES 特性
AD-6800	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	55±2	55,000±5,000	4-6	4.1	0	Lamination of PVC Sheet and Plywood, Applicable in Particle Wood PVC 皮與合板之貼合膠料適用於縮合板	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-6800L	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	55±2	25,000±5,000	4-6	3.4	0	Lamination of PVC Sheet and Plywood, Applicable in Multilayer Wood PVC 皮與合板之貼合膠料適用於積層板	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-6600	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	51±2	80,000±15,000	4-6	3.5	0	Lamination of PVC Sheet and Plywood, Applicable in Particle Wood PVC 皮與合板之貼合膠料適用於縮合板	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-4000	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	50±2	65,000±10,000	4-6	3.2	0	Lamination of PVC Sheet and Plywood, Applicable in Cabinet (Ex. Speaker Case) PVC 皮與合板之貼合膠料適用於木箱製品(如喇叭箱)	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-4000L	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	50±2	14,000±3,000	4-6	3.9	0	Lamination of PVC Sheet and Plywood, Aluminum Foil and Paper PVC 皮與合板之貼合膠料, 鋁箔與紙張之貼合膠料	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-2000H	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	47±2	60,000±12,000	4-6	3.4	0	Lamination of PVC Sheet and Plywood PVC 皮與合板之貼合膠料	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-2000	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	White Emulsion 白色乳膠	47±2	20,000±2,000	4-6	3.1	0	Lamination of PVC Sheet and Plywood PVC 皮與不織布/紡織品之貼合膠料	Excellent Bonding Strength with PVC Sheet and good Heat Resistance 與 PVC 皮之接著力強,耐熱性良好
AD-1500	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	50±2	375±75	4-6	2.8	0	Adhesion for Cigarette Holder in High Speed Operation 高速煙支封口用膠	Good Mechanical Stability and Bonding Strength 機械穩定性良好, 接著力大, 高速接著
AD-1050	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	51±2	100±300	4-6	2.8	0	For Paper Tube Making and General Purpose 紙張接著, 一般接著	Drying Speed and Excellent Bonding Strength 乾燥速度快, 接著力大
AD-600T	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	60±2	4,000±1,000	4-6	2.8	0	Water Proof for Concrete 混凝土用防水劑	High Concentration, Good Concrete Miscibility and Water Proof 高固型份, 與混凝土混合性良好, 防水性佳
AD-550T	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	3,500±1,000	4-6	3.2	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好, 防水性佳
AD-550K	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	4,750±750	4-6	3.2	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好, 防水性佳
AD-550J	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	3,000±1,000	4-6	2.7	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好, 防水性佳
AD-68T	Ethylene Vinyl Acetate Copolymer 乙烯-醋酸乙稀共聚樹脂	Milky White 白色乳膠	55±2	2,500±500	4-6	2.7	0	Water Proof for Concrete 混凝土用防水劑	Good Concrete Miscibility and Water Proof 與混凝土混合性良好, 防水性佳